



PRODUCT **SELECTION GUIDE**

Innovative and customized solutions
that meet your needs

Honeywell

HONEYWELL SPECIALTY ADDITIVES PRODUCT LIST

PROPERTIES						
TYPICAL PROPERTIES OF A-C® POLYETHYLENES & COPOLYMERS	METTLER DROP POINT (ASTM D-3954)	HARDNESS DMM (ASTM D-5)	DENSITY G/CC (ASTM D-1505)	VISCOSITY CPS @ 140°C (BROOKFIELD)	ACID NUMBER MG KOH/G (ASTM D-1386)	PHYSICAL FORM
HOMOPOLYMERS						
A-C 3A	112°C 234°F	2.0	0.92	450	Nil	Powder
A-C 6, 6A	106°C 223°F	4.0	0.92	375	Nil	Prills, Powder
A-C 8, 8A	113°C 235°F	1.0	0.93	450	Nil	Prills, Powder
A-C 9, 9A, 9F	115°C 239°F	0.5	0.93	450	Nil	Prills, Powder, Fine Powder
A-C 16, 16A	102°C 216°F	5.5	0.91	525	Nil	Prills, Powder
A-C 617, 617A	101°C 214°F	7.0	0.91	180	Nil	Prills, Powder
A-C 1810A	121°C 250°F	1.0	0.95	20	Nil	Powder
A-C 820A	126°C 259°F	<0.5	0.96	80	Nil	Powder
A-C 725P	110°C 230°F	3.5	0.92	1400	Nil	Powder
A-C 1702	90°C 194°F	98.0 ⁽¹⁾	0.88	30	Nil	Greased-like, Slab
A-C 1375	106°C, 223°F	<0.5	0.92	375	Nil	Prills
OXIDIZED HOMOPOLYMERS						
A-C 629, 629A	101°C 214°F	5.5	0.93	200	15	Prills, Powder
A-C 656	98°C 208°F	9.0	0.92	185	15	Prills
A-C 673P	110°C 230°F	<1.0	0.95	400	17	Powder, Pastilles
A-C 680, 680A	108°C 226°F	1.5	0.93	250	16	Prills
A-C 6702P	88°C 190°F	90.0 ⁽¹⁾	0.85	35	15	Grease-like
A-C 680P	108°C 226°F	<1.0	0.93	450	17	Pastilles
HIGH-DENSITY OXIDIZED HOMOPOLYMERS						
A-C 307, 307A	140°C 284°F	<0.5	0.98	85000 ⁽²⁾	7	Granule, Powder
A-C 316, 316A	140°C 284°F	<0.5	0.98	8500 ⁽²⁾	16	Granule, Powder
A-C 325	136°C 277°F	<0.5	0.99	4400 ⁽²⁾	25	Granule
A-C 330	137°C 279°F	<0.5	0.99	3600 ⁽²⁾	30	Granule
A-C 392	138°C 280°F	<0.5	0.99	4500 ⁽²⁾	30	Granule
COPOLYMERS/ ETHYLENE-ACRYLIC ACID						
A-C 540, 540A	105°C 221°F	2.0	0.93	575	40	Prills, Powder
A-C 580	95°C 203°F	4.0	0.94	650	75	Prills
A-C 5120	92°C 198°F	8.0	0.94	650	120	Prills
COPOLYMERS/ETHYLENE-VINYL ACETATE						
A-C 400, 400A	92°C 198°F	9.5	0.92	595	13% Vinyl Acetate	Prills, Powder
A-C 405M	100°C 212°F	5.0	0.92	600	8.5% Vinyl Acetate	Prills
A-C 405T	102°C 216°F	4.0	0.92	600	6% Vinyl Acetate	Prills
OXIDIZED COPOLYMER						
A-C 645P	100°C 212°F	5.0	0.94	375	13 (SAP=56) ⁽³⁾	Pastilles

GRADE

PROPERTIES					
ACLYN® LOW MOLECULAR WEIGHT IONOMERS	MELTING POINT ⁽⁴⁾	CATION TYPE	ACID NUMBER MG KOH/G (ASTM D-1386)	VISCOSITY CPS @ 190°C (BROOKFIELD)	PHYSICAL FORM
ETHYLENE MALEIC ANHYDRIDE COPOLYMERS					
AClyn 201A*	102°C 215°F	Ca	42	5500	Powder
AClyn 285P*	82°C 180°F	Na	20	80000	Granule
AClyn 295P*, 295A*	99°C 210°F	Zn	Nil	4500	Granule, Powder

GRADE

*Make to Order Product

PROPERTIES						
ACUMIST® MICRONIZED POLYOLEFIN WAXES	METTLER DROP POINT (ASTM D-3954)	HARDNESS DMM (ASTM D-5)	DENSITY G/CC (ASTM D-1505)	AVERAGE PARTICLE SIZE MICRONS	ACID NUMBER MG KOH/G (ASTM D-1386)	PHYSICAL FORM
PE MICRONIZED WAXES						
ACumist A-6*	137°C 279°F	<0.5	0.99	6	26-40	Micronized Powder
ACumist A-12	137°C 279°F	<0.5	0.99	12	26-40	Micronized Powder
ACumist A-45*	137°C 279°F	<0.5	0.99	30	26-40	Micronized Powder
ACumist B-6	126°C 259°F	<0.5	0.96	6	Nil	Micronized Powder
ACumist B-9*	126°C 259°F	<0.5	0.96	9	Nil	Micronized Powder
ACumist B-12	126°C 259°F	<0.5	0.96	12	Nil	Micronized Powder
ACumist B-18*	126°C 259°F	<0.5	0.96	18	Nil	Micronized Powder
ACumist C-5*	121°C 250°F	1.0	0.95	5	Nil	Micronized Powder
ACumist C-12*	121°C 250°F	1.0	0.95	12	Nil	Micronized Powder
ACumist C-18*	121°C 250°F	1.0	0.95	18	Nil	Micronized Powder
ACumist D-6*	118°C 244°F	1.5	0.95	6	Nil	Micronized Powder
ACumist D-9	118°C 244°F	1.5	0.95	9	Nil	Micronized Powder
ACumist P-5*	145°C 293°F	<0.5	0.91	5	Nil	Micronized Powder
PTFE MICRONIZED WAX BLENDS ⁽⁵⁾						
ACumist 3105G*	121°C 250°F	<1.5	1.1	5	Nil	Micronized Powder
ACumist 3405G*	121°C 250°F	<1.0	0.95	5	Nil	Micronized Powder

*Make to Order Product

PROPERTIES						
MODIFIED OLEFIN PRODUCTS	METTLER DROP POINT (ASTM D-3954)	HARDNESS DMM (ASTM D-5)	DENSITY G/CC (ASTM D-1505)	VISCOSITY CPS @ 140°C (BROOKFIELD)	SAPONIFICATION NUMBER MG KOH/G	PHYSICAL FORM
ETHYLENE MALEIC ANHYDRIDE COPOLYMERS						
A-C 573A, 573P	106°C 223°F	4.5	0.92	600	5	Powder, Pastilles
PROPYLENE MALEIC ANHYDRIDE COPOLYMERS						
A-C 596P	143°C 290°F	<0.5	0.94	<400 @ 190°C	43	Powder, Pastilles
A-C 597P	143°C 290°F	<0.5	0.94	500 @ 190°C	80	Powder, Pastilles
A-C 950P	153°C 307°F	<0.5	0.93	2000 @ 190°C	43	Pastilles
A-C 907P	152°C 306°F	<0.5	0.93	350	87	Pastilles
A-C 1325P	149°C 300°F	<0.5	0.92	1600	18	Pastilles

PROPERTIES						
POLYPROPYLENE HOMOPOLYMERS	METTLER DROP POINT (ASTM D-3954)	HARDNESS DMM (ASTM D-5)	DENSITY G/CC (ASTM D-1505)	VISCOSITY CPS @ 140°C (BROOKFIELD)	SAPONIFICATION NUMBER MG KOH/G	PHYSICAL FORM
A-C 1754	163°C	0.5	0.89	750	Nil	Powder
A-C 1089	146°C 295°F	<0.5	0.91	45	Nil	Powder

*Make to Order Product

Notes:

- (1) ASTM D-1321
- (2) Measured at 150°C
- (3) Saponification No., mg KOH/g
- (4) Determined by Differential Scanning Calorimetry.
- (5) Drop Point listed is the initial melt point of the PE Wax only. PTFE does not melt but will decompose above 615°F

ENVIRONMENTAL CONSIDERATIONS

A-C polyethylenes and specialty additives are essentially inert and insoluble in water. Materials may be disposed of as non-hazardous solid organic waste. Spillage is not expected to cause adverse environmental effects.

SAFETY PRECAUTIONS

A-C polyethylenes and specialty additives are non-hazardous at ambient temperatures. Consult Material Safety Data Sheets for complete information.

PACKAGING/SHIPPING

A-C polyethylenes and specialty additives are normally supplied in 25 kg four-ply kraft bags or 50 kg drums depending on the product. Products in bags are shipped on pallets. 40 bags to a pallet, net weight 1,000 kgs, and stretched-wrapped. Pallet loads are approximately 129.54 cm long, 111.76 cm wide, and up to 144.78 cm high, depending on product and bulk density. Bulk bags are available in a variety of sizes to meet customer requirements.

For additional information or to contact us, please visit:

<https://industrial.honeywell.com/us/en/applications/specialty-additives>



All statements and information provided herein are believed to be accurate and reliable, but are presented without guarantee, warranty or responsibility of any kind, express or implied. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement, and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated herein, or that other measures may not be required. User assumes all liability for use of the information and results obtained.

BRO-22-57-EN | 08/22
© 2022 Honeywell International Inc.

**THE
FUTURE
IS
WHAT
WE
MAKE IT**

Honeywell